

High-Quality Brown Testliner: Made from 100% recycled fibres.
Presents and protects the final product with the best optical effect.



Grade description	Basic Weight g/m ²	Burst strength kPa		SCT CD kN/m	
Test method	ISO 536	ISO 2758		ISO 9895	
Tolerance	± 3%	Guaranteed	Target	Guaranteed	Target
VPK Liner 90 g/m ²	90	180	200	1.35	1.50
VPK Liner 100 g/m ²	100	200	220	1.55	1.75
VPK Liner 110 g/m ²	110	220	240	1.70	1.90
VPK Liner 120 g/m ²	120	240	260	1.80	2.00
VPK Liner 130 g/m ²	130	260	280	1.95	2.20
VPK Liner 135 g/m ²	135	270	290	2.05	2.30
VPK Liner 150 g/m ²	150	300	320	2.25	2.50
VPK Liner 160 g/m ²	160	300	320	2.35	2.65
VPK Liner 175 g/m ²	175	330	350	2.55	3.00
VPK Liner 200 g/m ²	200	380	400	2.90	3.25

Moisture content: 7.5 ± 1.5% (ISO 287)
Cobb 60: Maximum 50g/m² - Target 35g/m² (ISO 535)
Test conditions: 23°C - 50% RH (ISO 187)

Issue date: 02.2026



High-Quality Recycled Fluting: Made from 100% recycled fibres.

Lightens the final product with the best runability.



Grade Description	Basic Weight g/m ²	CMT 30 N		SCT CD kN/m	
Test method	ISO 536	ISO 7263		ISO 9895	
Tolerance	± 3%	Guaranteed	Target	Guaranteed	Target
VPK Flute 80 g/m ²	80		110	1.20	1.30
VPK Flute 85 g/m ²	85		120	1.30	1.40
VPK Flute 90 g/m ²	90		130	1.40	1.55
VPK Flute 100 g/m ²	100	140	150	1.55	1.75
VPK Flute 110 g/m ²	110	155	165	1.75	1.95
VPK Flute 120 g/m ²	120	170	180	1.85	2.00
VPK Flute 130 g/m ²	130	180	190	2.00	2.25
VPK Flute 135 g/m ²	135	190	200	2.10	2.35
VPK Flute 150 g/m ²	150	210	225	2.25	2.5
VPK Flute 160 g/m ²	160	220	235	2.40	2.65
VPK Flute 170 g/m ²	170	230	245	2.50	2.85

Moisture content: 8.0 ± 1.5% (ISO 287)
 Test conditions: 23°C - 50% RH (ISO 187)

Issue date: 02.2026



High-Performance Recycled Fluting: Made from 100% recycled fibers.
 Provides the final product with extra strength at low grammages.



Grade Description	Basic Weight g/m ²	CMT 30 N		SCT CD kN/m	
		Guaranteed	Target	Guaranteed	Target
Test method	ISO 536	ISO 7263		ISO 9895	
Tolerance	± 3%	Guaranteed	Target	Guaranteed	Target
VPK Flute HP 105 g/m ²	105	175	185	1.90	2.00
VPK Flute HP 115 g/m ²	115	190	200	2.10	2.20
VPK Flute HP 120 g/m ²	120	200	210	2.20	2.30

Moisture content: 8.0 ± 1.5% (ISO 287)
 Test conditions: 23°C - 50% RH (ISO 187)

Issue date: 02.2026



High-Performance double-use paper: Made from 100% recycled fibres.
Combining Fluting and Testliner to reduce paper stock.



Grade Description	Basic Weight g/m ²	Burst strength kPa		CMT 30 N		SCT CD kN/m	
Test method	ISO 536	ISO 2758		ISO 7263		ISO 9895	
Tolerance	± 3%	Guaranteed	Target	Guaranteed	Target	Guaranteed	Target
VPK One 80 g/m ²	80	150	170		110	1.20	1.30
VPK One 85 g/m ²	85	170	190		120	1.30	1.40
VPK One 100 g/m ²	100	200	220	140	150	1.60	1.80
VPK One 110 g/m ²	110	220	240	155	165	1.75	1.95
VPK One 125 g/m ²	125	250	270	175	185	2.00	2.25
VPK One 135 g/m ²	135	270	290	190	200	2.10	2.35
VPK One 160 g/m ²	160	310	330	220	230	2.40	2.60

Moisture content: 7.5 ± 1.5% (ISO 287)

If basic weight >= 100 g/m² Cobb 60: Maximum 50g/m² - Target 35g/m² (ISO 535)

Test conditions: 23°C - 50% RH (ISO 187)

Issue date: 02.2026

